



Scotchcal™ Opaque Graphic Film

Series 80

Product Bulletin

Product Description

These excellent cast films are a range of colored films that have been specially developed to be knife cut on electronic systems. The film range is available in 84 colors including 8 metallic tones.

3M™ Scotchcal™ Opaque Graphic Film Series 80 have good conformability for application on flat or moderate curved surfaces, with or without rivets.

They are excellent for easy cutting of small letters or complex graphics.

Product Line Electrocut 80-X X = color code, opaque, glossy (and few matte), permanent adhesive.

Product Characteristics

These are typical values for unprocessed products.
Contact your 3M representative for a custom specification.

Physical & Application

Material	cast vinyl	
Surface finish	glossy and matte (see product line)	
Thickness (film)	50 µm (0.05 mm)	
Adhesive type	solvent acrylic; pressure-sensitive	
Adhesive appearance	clear	
Liner	glassine paper	
Adhesion	approx. 20 N/25 mm	FTM 1: 180° peel, substrate: glass; cond: 24 h 23°C/50%RH
Application method	wet or dry	
Applied shrinkage	< 0.2 mm	FTM 14
Application temperature	+8°C	minimum (air and substrate)
Service temperature	-40°C to +95°C	
Surface type	flat to curved, incl. rivets	
Substrate type	aluminum, glass, PMMA, PC*, ABS, paint	

PC*: Might require drying with heat before use

Graphic removal Fair to remove with heat and/or chemicals from supported substrates.
No liability is given for ease or speed of removal of any graphic. Pay attention to adequate air and substrate temperature.

Storage Shelf life Use within two years from the date of manufacture on the sealed original box.
Use within one year after opening the box.

Storage conditions +4°C to +40°C, out of sunlight, original container in clean and dry area.

Flammability Classified according to DIN EN 13501-1 reaction to fire performance as B / s1 / d0

Durability

Unprocessed film

The following durability data are given for unprocessed film only!

Climatic zones

Graphic durability is largely determined by the climate and the angle of exposure. Find below a table showing the durability of a product according to the angle of exposure and the geographical location of the application.


Zone 1 Northern Europe, Italy (north of Rome), Russia

Zone 2 Mediterranean area without North Africa, South Africa

Zone 3 Gulf area, Africa

Exposure types

Vertical:



The face of the graphic is $\pm 10^\circ$ from vertical.

Interior

Interior means an application inside a building without direct exposure to sunlight.

Vertical outdoor exposure

white/black
colors
transparent
metallics

Zone 1

10 years
8 years
5 years
4 years

Zone 2

8 years
6 years
4 years
3 years

Zone 3

6 years
4 years
3 years
2 years

Interior application

interior

Zone 1

10 years

Zone 2

10 years

Zone 3

10 years

Limitations of End Uses

3M specifically does not recommend or warrant the following uses, but please contact us to discuss your needs to recommend other products.

Graphics applied to

- flexible substrates incl. 3M™ Panaflex™ Awning and Sign Facing 945GPS and 3M™ Panagraphics™ III Wide Width Flexible Substrate.
- low surface energy substrates or substrates with low surface energy coating.
- other than flat or moderate curved/corrugated surfaces.
- painted or unpainted wallboards, gypsum boards and wallpapers.
- stainless steel.
- surfaces not clean and more than moderate textured.
- surfaces with poor paint to substrate adhesion.

Graphic removal from

- signs or existing graphics that must remain intact.

Graphics subjected to

- gasoline vapors or spills.

Important Notice

- 3M Commercial Graphics Division products are not tested against automotive manufacturer specifications!
- Non vertical applications will have a significant decrease in durability!
- Thermoforming of applied film is not recommended!
- 3M accepts no liability for glass breakage when using this film for window graphics.
- To avoid color variations all pieces of applied film of one colored area should be processed out of one lot of material.
- The color appearance of metallic film is dependent on the viewing angle to the product! Therefore the job design should be done that all parts of metallic film are applied the same orientation.

Graphics Manufacturing

Shipping finished graphics

Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

Converting Information

Electronic Cutting

	Based upon cutting evaluations the minimum height for text is 10 mm using upper and lowercase Helvetica Medium. The stroke width should not be lower than 1 mm.
	The variable characteristics of electronically controlled cutting equipment require users to verify their specific requirements.
Sharpness of knife blade	Dull blades impart a serrated look to the edge of the cut film.
Weight of knife blade	The ideal weight slightly scores the liner. Too little weight does not cut completely through the film and the adhesive. Excessive weight cuts the liner and causes the blade to drag, accelerating wear and creating a serrated cut edge on the film.
Weeding	The excess film should be weeded (removed) as soon after cutting as practical. This is to minimize the effect of possible adhesive flow.
Temperature and relative humidity	Temperature and relative humidity are minor considerations, but avoid extreme or rapid fluctuating conditions.
Roll storage	Store the film in the same environment as the cutting equipment.
Further information	For more details refer to our instruction bulletin 4.1 'Sheeting, Scoring, Film Cutting', please. >Instruction Bulletin 4.1'Sheeting, Scoring, Film cutting'<

Application

See product bulletin ATR 'application tape recommendations' for information about selection and use of suitable application tapes for this product, please.

[> Product Bulletin Application Tape Recommendations <](#)

Refer to Instruction Bulletin 5.1 'select and prepare substrates for graphic application', for general application information.

[>Instruction Bulletin 5.1 'select and prepare substrates for graphic application'<](#)

Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline).

Refer to Instruction Bulletin 6.5 'storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.

[>Instruction Bulletin 6.5 'Storage, Handling, Maintenance and Removal of Films and Sheetings'<](#)

Remarks

	This bulletin provides technical information only.
Important notice	All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law. Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.
Additional Information	Visit the web site of your local subsidiary at www.3Mgraphics.com for getting more: <ul style="list-style-type: none">- details about 3M™ MCS™ Warranty and 3M Performance Guarantee- additional instruction bulletins- a complete product overview about materials 3M is offering



Commercial Solutions Division

Hermeslaan 7
1831 Diegem, Belgium

Responsible for this technical bulletin

3M Deutschland GmbH | Safety & Graphics Laboratory
Carl-Schurz-Str. 1 | 41453 Neuss, Germany

3M, Controllac, Envision, Panagraphics, Panaflex, Scotchcal, Comply and MCS are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.