





Date of issue : 27/08/2008 Last. mod. date : 27/08/2008

Product code

02038 RI-205/80 PVC GLOSS CLEAR AR 801 WK 135

Description

Gloss clear plasticised vinyl film, with good flexibility and conformability on curved surfaces.

Printing methods: solvent based and UV screenprinting, offset UV, hot stamping.

Removable adhesive with easy and clean removability from glass and from many substrates. Not recommended for paper, PVC, ABS, PS, air dried paints and varnish.

Temporary marking, instructions and promotional information labels.

Technical data

FACE MATERIAL

 $\begin{array}{lll} \mbox{Type} & \mbox{Plasticised vinyl film} \\ \mbox{Colour and Finish} & \mbox{Clear, Gloss} \\ \mbox{Weight} & \mbox{104g/m}^2 \\ \mbox{Thickness} & \mbox{80} \mbox{μ} \\ \end{array}$

ADHESIVE

Reference AR 801

Type Acrylic removable

Min. Appl. Temp. +5°C

Service Temp. $-40^{\circ}\text{C}/+120^{\circ}\text{C}$

 $\begin{array}{lll} \mbox{Shear} & \mbox{High} \\ \mbox{Tack FTM9} & 2\mbox{N/inch}^2 \\ \mbox{FinAdh FTM2} & 2\mbox{N/inch} \end{array}$

RELEASE BACKING

Type 1 side silicone coated kraft

CHEMICAL RESISTANCE

Detergent No effect (24 Hrs)
Gasoline No effect (1 Hrs)
SAE20 Motoroil No effect (24 Hrs)
10% HCI No effect (10 min)
10% NH4OH No effect (10 min)

Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in pdf data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.